

ION EXCHANGE RESIN

PersaLite™ MXB10

Mixture of Strong Acid Cation & Strong Base Anion

DESCRIPTION AND APPLICATIONS

PersaLiteTM MXB10 is a gaussian, gel, ready-to-use, mixture of strong acid cation and strong base anion exchange resin for demineralization applications in mixed bed and single-use systems. This pre-mixed resin is also widely used in Electrical Discharge Machining (EDM) application.

SPECIFICATIONS

Copolymer: Styrene-divinylbenzene

Matrix: Gel

Functional Group: Sulfonic Acid / Quaternary Ammonium – Type II

Physical Form: Misture of White and Yellow beads

Ionic Form: H^+/OH^-

Total Capacity: $\geq 1.9 / 1.0 \text{ eq/L}$ Moisture Content: 57 - 67 %Particle Size: $300 - 1,200 \mu\text{m}$

Uniformity Coefficient: ≤ 1.7 Cation / Anion Volumetric Ratio: 50% / 50% Whole Beads Count: ≥ 95% Particle Density: 1.15 g/mL

Bulk Density: 730 g/L (45.6 lb/ft³)

SUGGESTED OPERATING CONDITIONS

Temperature Range: 100°C (212°F) (Non-Regenerable Bed)

60°C (140°F) (Mixed Bed)

pH Range: 1-14

Notes: The information and data are in good faith but without guarantee. Please consult our engineering team for more information before installing and operating the resin. Modifications of the specifications can occur without prior notice. IX resins should be stored in sealed bags in areas with a temperature above 0°C. See MSDS for safety issues.

PERSALT: 401 East Jackson Street Suite 2340, Tampa, FL 33602 Phone: (813) 803-6125 Fax: (813) 803-6126 – info@persalt.com